


ANCORSTEEL 30 HP



This is a water atomized, prealloyed, low alloy steel powder for high performance applications. The prealloyed 0.30 weight % molybdenum addition results in moderate hardenability, suitable for heat treated applications. This material conforms to MPIF standard 35 for FL - 390X type materials.

www.gknpm.com


Nominal Chemistry (weight %)

Iron	Manganese	Molybdenum
Bal.	0.15	0.30

Typical Particle Size (weight %)


Micrometers	+250	-250/+150	-150/+45	-45
U.S. Standard Mesh	(+60)	(-60/+100)	(-100/+325)	(-325)
	Trace	10	70	20

Green Density



(with 0.75 wt% EBS)

Green Strength




(with 0.75 wt% EBS)

© GKN Powder Metallurgy

This document is for informational purposes only and should not be considered as a binding description of the products or their performance in all applications. The product characteristics and performance data on this page represent standard products and depict their typical performance under controlled laboratory conditions. Actual performance will vary depending on the operating environment and application. GKN Powder Metallurgy reserves the right to revise its products and documents without notification. For product design to meet specific applications, dimensions, electrical and working points, please contact GKN Powder Metallurgy Marketing and Sales.

ANCORSTEEL 30 HP

Transverse Rupture Strength Properties




(with 0.6 wt% graphite + 0.75 wt% EBS)

■ 30 HP

■ 30 HP + 2% Nickel

Tensile Properties



(with 0.6 wt% graphite + 0.75 wt% EBS)

All test specimens were compacted to 7.0 g/cm^3 and sintered at $1120 \text{ }^\circ\text{C}$ ($2050 \text{ }^\circ\text{F}$) in $90\text{N}_2\text{-}10\text{H}_2$ atmosphere with conventional cooling.

© GKN Powder Metallurgy

This document is for informational purposes only and should not be considered as a binding description of the products or their performance in all applications. The product characteristics and performance data on this page represent standard products and depict their typical performance under controlled laboratory conditions. Actual performance will vary depending on the operating environment and application. GKN Powder Metallurgy reserves the right to revise its products and documents without notification. For product design to meet specific applications, dimensions, electrical and working points, please contact GKN Powder Metallurgy Marketing and Sales.